

Thermal Interface - Wet Dispensed

Dow Corning[®] SC 102 Compound

White, non-curing and non-flowing thermally conductive compound

FEATURES

- Non-flowing
- Moderate thermal conductivity

BENEFITS

- No need for ovens or curing
- Heat flow away from electronic components can increase reliability

POTENTIAL USES

- Gap fill material between electronic heat sources and heat sinks
- Thermal dissipation in a wide array of industrial applications such as power supplies

APPLICATION METHODS

- Apply grease with a squeegee through a stencil or screen
- Spread out bulk material with a spatula

TYPICAL PROPERTIES

Specification Writers: Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

| Property | Unit | Value |
|-----------------------------|-----------------------|--------------|
| Viscosity | cP | 29000 |
| | mPa-sec | 29000 |
| | Pa-sec | 29 |
| Specific Gravity (Uncured) | - | 2.4 |
| Penetration (unworked) | 1/10 mm | 315 |
| Thermal Resistance @ 40 psi | °C*cm ² /W | 0.62 |
| Volatile Content | % | 0.29 |
| Bleed | % | 0.14 |
| Evaporation | % | 0.26 |
| Shelf Life @ 32C | months | 24 |

DESCRIPTION

Dow Corning thermally conductive compounds are greaselike silicone materials, heavily filled with heat-conductive metal oxides. This combination promotes high thermal conductivity, low bleed and high-temperature stability. The compounds resist changes in consistency at temperatures up to 177°C (350°F), maintaining a positive heat sink seal to improve heat transfer from the electrical/electronic device to the heat sink or chassis, thereby increasing the overall efficiency of the device. Long-term, reliable protection of sensitive circuits and components is important in many of today's delicate and demanding electronic applications. With the increase in processing power and the trend toward smaller, more compact electronic modules, the need for thermal management is growing. Thermally conductive silicones function as heat transfer media, durable dielectric insulation, barriers against environmental contaminants and as stress-relieving shock and vibration absorbers over a wide temperature and humidity range. In addition to sustaining their physical and electrical properties over a broad range of operating conditions, silicones are resistant to ozone and ultraviolet degradation and have good chemical stability. Good heat transfer is dependent on a good interface between the heat producing device and the heat transfer media. Silicones have a low surface tension that enables them to wet most surfaces, which can lower the thermal contact resistance between the substrate and the material.

SOLVENT EXPOSURE

Although highly filled silicones such as those discussed in this data sheet are generally more resistant to solvent or fuel exposure, standard silicones are intended only to survive splash or intermittent exposures. Testing

should be done to confirm performance of the adhesives in the application and under the specified environmental conditions.

STORAGE AND SHELF LIFE

Shelf life is indicated by the "Use By" date found on the product label. For best results, Dow Corning thermally conductive materials should be stored at or below the maximum specified storage temperature. Special precautions must be taken to prevent moisture from contacting these materials. Containers should be kept tightly closed and head or air space minimized. Partially filled containers should be purged with dry air or other gases, such as nitrogen. Any special storage and handling instructions will be printed on the product containers.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.dowcorning.com, or consult your local Dow Corning representative.

LIMITATIONS

These products are neither tested nor represented as suitable for medical or pharmaceutical uses.

LIMITED WARRANTY INFORMATION PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this

information should not be used in substitution for customer's tests to ensure that Dow Corning's products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent. Dow Corning's sole warranty is that the product will meet the Dow Corning sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

SAFE HANDLING INFORMATION

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. THE MATERIAL SAFETY DATA SHEET IS AVAILABLE ON THE DOW CORNING WEBSITE AT WWW.DOWCORNING.COM, OR FROM YOUR DOW CORNING REPRESENTATIVE, OR DISTRIBUTOR, OR BY CALLING YOUR GLOBAL DOW CORNING CONNECTION.

For More Information

To learn more about these and other products available from Dow Corning, please visit the Dow Corning Electronics website at www.dowcorning.com/electronics.



Electronics
Solutions

Dow Corning and Sylgard are registered trademarks of Dow Corning Corporation. All other trademarks or brand names are the property of their respective owners. ©2008 Dow Corning Corporation. All rights reserved. Printed in USA Form No. 11-1333A-01